## '99 춘계학술발표회 논문집 한국원자력학회

Nb<sub>2</sub>O<sub>5</sub> 및 산소 포텐샬이 Simulated U<sub>3</sub>O<sub>8</sub> 분말 성형체의 치밀화에 미치는 영향 Effects of Nb<sub>2</sub>O<sub>5</sub> and Oxygen Potential on Densification of Simulated U<sub>3</sub>O<sub>8</sub> Powder Compacts

## 김 건식, 김 영민 한국원자력연구소

## 요 약

Nb<sub>2</sub>O<sub>5</sub> 및 산소 포텐샬이 simulated U<sub>3</sub>O<sub>8</sub> 분말 성형체의 치밀화에 미치는 영향을 연구하였다. Simulated U<sub>3</sub>O<sub>8</sub>에 첨가제를 넣지 않은 성형체와 0.5wt% Nb<sub>2</sub>O<sub>5</sub>를 첨가한 성형체를 1700°C에서 -520~-390kJ/mole 범위의 산소 포텐샬로 소결하였다. 첨가제를 넣지 않은 simulated 소결체는 산소 포텐샬에 무관하게 밀도가 7.5 g/cm³인 반면, 0.5wt% Nb<sub>2</sub>O<sub>5</sub>를 첨가한 소결체는 산소 포텐샬이 증가할수록 밀도가 7.3에서 10.37g/cm³으로 급격히 증가한다. 이 것은 CO<sub>2</sub>/H<sub>2</sub>=0.02 분위기에서 소결하는 동안 Nb<sub>2</sub>O<sub>5</sub>가 NbO<sub>2</sub>로 환원되고, Nb<sup>4+</sup> 이온이 UO<sub>2</sub> 격자에 침입형으로 고용되면서 우라늄 공공의 농도가 증가하기 때문이다. Simulated U<sub>3</sub>O<sub>8</sub>에 0.3wt% Nb<sub>2</sub>O<sub>5</sub>를 첨가한 성형체를 가열중 알곤(Ar) 분위기로 900°C에서 1시간 유지시킨 후동일한 조건에서 소결하면 밀도가 10.53 g/cm³로 증가한다

## Abstract

The effects of  $Nb_2O_5$  and oxygen potential on the densification of simulated  $U_3O_8$  powder compacts have been studied. The simulated  $U_3O_8$  compacts with and without 0.5wt%  $Nb_2O_5$  additions were sintered at  $1700^{\circ}C$  in the oxygen potentials ranging from -520kJ/mole to -390kJ/mole. It was found that the simulated  $UO_2$  pellet had a density of about 7.5 g/cm<sup>3</sup> and was independent of oxygen potentials. However, with 0.5wt%  $Nb_2O_5$  addition, the density was increased up to 10.37 g/cm<sup>3</sup>, dependent on the oxygen potentials. This enhancing effect of  $Nb_2O_5$  is supposed to be related with the increase in concentration of uranium vacancy, because  $NbO_2$  is interstitially dissolved in  $UO_2$ . The simulated  $U_3O_8$  compact with  $Nb_2O_5$  which had been annealed at  $900^{\circ}C$  for 1 hour in argon before sintering, achieved a higher density of 10.53 g/cm<sup>3</sup> and small grain size after sintering.