## STM Study on $c(4\times4)$ Reconstruction of Si(100)

<u>Jae Yeol Maeng</u>, Sehun Kim
Department of Chemistry
Korea Advanced Institute of Science and Technology

We have studied the atomic structure of Si(100)- $c(4\times4)$  reconstruction using scanning tunneling microscopy(STM). The  $c(4\times4)$  reconstruction can be formed by annealing the hydrogen exposured surface at temperatures between 850 and 960 K. At this temperature ranges, adsorbed hydrogen atoms are all desorbed. Therefore, the  $c(4\times4)$  reconstruction is due to the Si dimers on surface. The filled and empty state images of the STM were interpreted in terms of Si dimers in  $c(4\times4)$  primitive cell forming the reconstruction. Based on the STM images and hydrogen adsorption experiment on  $c(4\times4)$  surface, we suggest that Si dimers in  $c(4\times4)$  unit cell are perpendicular ad-dimer to the underlying Si dimer rows.