

## Synthesis and properties of organic light-emitting diodes using BECCIP material

HO-SIK LEE<sup>a</sup>, SANG-KEOL KIM<sup>b</sup>, WON-JAE LEE<sup>c</sup>, JONG-WOOK PARK<sup>d</sup>, TAE WAN KIM<sup>e</sup>  
AND DOU-YOL KANG<sup>a</sup>

<sup>a</sup> Dept. of Electrical and Control Engineering, Hongik University, Korea

<sup>b</sup> Dept. of Electrical Engineering, Kwangwoon University, Korea

<sup>c</sup> Dept. of Electronics, Kyungwon College, Korea

<sup>d</sup> Dept. of Polymer Engineering, Chungju University, Korea

<sup>e</sup> Dept. of Physics, Hongik University, Korea

### Abstract

We have synthesized the new blue electroluminescent material, Bis(3-N-ethylcarbazolyl)cyanoisophthalidene(BECCIP), and characterized its properties by UV/visible absorption, photoluminescent(PL) and electroluminescent(EL) spectrum. This material is well vacuum-deposited for thin film and has clear surfaced thin film property. The BECCIP shows blue PL and EL spectra at around at 485nm.

Keywords: Organic light-emitting diodes; BECCIP

### 1. INTRODUCTION

Recently, Tamoto et al., reported several bipolar emitting molecules with both an oxadiazole as an electron transport unit and a triphenylamine group as a hole transport unit[1]. When these units were incorporated into the molecular structure of emitting materials, the device using these molecules as an emitting layer showed improved electroluminescent characteristics. We were already reported of the Bis(3-N-ethylcarbazolyl) cyano-terephthalidene(BECCP) as a blue emitting material[2, 3]. In this paper, we report electrical and optical properties of BECCIP when it is used as an emissive layer in organic light-emitting diodes.

### 2. EXPERIMENTALS

Figure 1 shows a synthesis process and molecular structure of BECCIP. UV/visible absorption, PL and EL spectrum were measured using a HP8452A spectrophotometer and Perkin Elmer luminescence spectrometer LS50B. For EL device, the BECCIP were vacuum deposited on top of ITO-glass(Samsung Corning Co.) under  $10^{-6}$  torr, the rate of deposition was  $0.5\text{\AA}$  per second, an emitting area was  $15\text{mm}^2$  and aluminum layer was continuously deposited under the same vacuum condition

### 3. RESULTS AND DISCUSSION

Figure 2(a) shows the UV/visible absorption and PL spectrum of the BECCIP film on quartz substrate. The UV/Visible absorption bands are at 300, 320, and 390nm and blue PL at 485nm. Figure 2(b) shows a comparison of the PL of the BECCP and BECCIP. The PL intensity of BECCIP is stronger than that of






FIGURE 1. Synthesis of BECCIP.

BECCP at the same film thickness, which indicates that the BECCIP is more appropriate candidate than BECCP for blue-emitting material.

voltage is around at 8V.



(a) UV/visible and PL spectrum of BECCIP



(b) Comparison of PL intensity of the BECCP and BECCIP

FIGURE 2. UV/visible absorption, PL spectrum (a) of the BECCIP and comparison of PL intensity (b) of the BECCP and BECCIP.

A conventional EL device was fabricated using vacuum( $10^{-6}$  torr) deposited BECCIP emitting layer and Al electrode. Figure 3 shows a ITO/BECCIP/Al device shows blue light EL spectrum at 485nm and typical rectifying diode characteristics. The operation




FIGURE 3. EL spectrum of ITO/BECCIP/Al structure.

Figure 4 shows a current density-voltage( $J$ - $V$ ) characteristics in ITO/BECCIP(30, 60, 100nm)/Al devices. We observed that a turn-on voltage was decreased with a decrease of the film thickness.




FIGURE 4. Current density-voltage( $J$ - $V$ ) characteristics in ITO/BECCIP(30, 60, 100 nm)/Al devices.

#### 4. CONCLUSION

We synthesized the new blue material as a BECCIP, and observed PL and EL spectrum with at 485nm. Also, we compared the PL of the BECCP and

BECCIP. The PL intensity of BECCIP is stronger than that of BECCP, which means that the BECCIP is better candidate than BECCP for blue-emitting material.

#### Acknowledgment

This work was supported by Korea Research Foundation Grant (KRF-99-005-E00018).

#### References

- [1] N. Tamoto, C. Adachi and K. Nagai, *Chem. Mater.*, **9** (1997) 1077.
- [2] H.K. Kim, M.K. Ryu, K.D. Kim, and J.W. Park, *Macromolecules*, **31**, (1998) 1114.
- [3] J. W. Park, J. H. Lee, H. S. Lee, D. Y. Kang, T. W. Kim, *Thin Solid Films*, **363** (2000) 90.