

**SiO<sub>2</sub> RF Power와 증착 시간 변화에 따른 고유전 TiO<sub>2</sub>-SiO<sub>2</sub> 절연막의 특성  
(Effects of SiO<sub>2</sub> RF Power and Deposition Time in High-*k* TiO<sub>2</sub>-SiO<sub>2</sub> Dielectric Layers)**

김성연, 함문호, 명재민<sup>†</sup>

연세대학교 신소재공학과  
(jmmyoung@yonsei.ac.kr<sup>†</sup>)

MOSFET소자의 성능 향상을 위해 SiO<sub>2</sub> 절연막 두께를 감소시키게 되면 터널링 효과에 의한 누설 전류의 증가와 같은 문제점들이 발생한다. 이러한 문제점을 해결하기 위하여 SiO<sub>2</sub> 를 Al<sub>2</sub>O<sub>3</sub>, ZrO<sub>2</sub>, HfO<sub>2</sub>, Ta<sub>2</sub>O<sub>5</sub>, TiO<sub>2</sub> 와 같은 높은 유전상수를 갖는 게이트 절연 물질로 대체하려는 연구가 활발하게 진행되고 있다. 하지만 게이트 절연 물질로서 상대적으로 높은 밴드 갭 에너지를 가지는 SiO<sub>2</sub> (9 eV) 와 높은 유전상수를 가지는 TiO<sub>2</sub> (*k*: 50 ~ 80) 를 합성한 게이트 절연 물질에 관한 연구는 많이 보고되지 않고 있다.

본 연구에서는 SiO<sub>2</sub> target 과 TiO<sub>2</sub> target 을 사용하여 *p*-type Si (100) 기판과 유리 기판 위에 SiO<sub>2</sub> target의 RF power 와 증착 시간의 변화를 주어 co-sputtering하였고, 이에 따른 TiO<sub>2</sub>-SiO<sub>2</sub> 게이트 절연막의 특성 변화를 분석하였다.

FESEM 분석을 통해 TiO<sub>2</sub>-SiO<sub>2</sub> 게이트 절연막 표면의 형상과 두께를 확인하였으며, XRD 분석을 통해 제작한 게이트 절연막의 결정학적 특성을 관찰하였다. XPS 분석을 통해서 SiO<sub>2</sub> target의 RF power와 증착 시간에 따른 Si, Ti, O 원자간 화학적 결합의 변화를 살펴보았다. 고유전 게이트 절연막으로서 TiO<sub>2</sub>-SiO<sub>2</sub> 박막의 적합성 여부를 확인하기 위하여 TiO<sub>2</sub>-SiO<sub>2</sub> 게이트 절연막 위에 sputter를 이용하여 Pt 전극을 형성한 후 I-V, C-V를 측정하였다. 또한 UV-VIS를 이용하여 유리기판 위에 증착한 절연막의 투과율을 분석하여 TiO<sub>2</sub>-SiO<sub>2</sub> 게이트 절연막의 TFT로의 응용 가능성을 확인하였다.

**Keywords:** TiO<sub>2</sub>, SiO<sub>2</sub>, co-sputtering, high-*k*, TFT

**Vertical Growth of Si Nanowires Via Control of Dilute Gas Ratio**

Han-Don Um, Yang-Gyoo Jung, Sang-Won Jee, Hong-Seok Seo, Jung-Ho Lee<sup>†</sup>

Dept. of Fine Chemical Engineering, Hanyang University  
(jungho@hanyang.ac.kr<sup>†</sup>)

Silicon nanowires(SiNWs) have received considerable attention such as field effect transistor and sensors. For ultra-large scale integration devices, SiNWs have to be grown vertically. We show that large-scale desired SiNWs have been synthesized by thermal chemical vapor deposition using SiCl<sub>4</sub> gas from 800 to 900°C varying the condition of H<sub>2</sub>/Ar ratio used as dilute gas. In H<sub>2</sub> rich or only Ar atmosphere, SiNWs are grown without substrate orientation dependence. SiNWs could be grown vertically when Ar/H<sub>2</sub> ratio is larger than 2. Scanning electron microscopy and Energy dispersive X-ray spectroscopy analysis have been employed to characterize the SiNWs.

**Keywords:** silicon nanowire, dilute gas, Ar, H<sub>2</sub>