

FA07

### Controlling Magnetism by Light

Theo Rasing

IMM, Radboud University Nijmegen, Toernooiveld 1, 6525 ED Nijmegen, The Netherlands  
Phone: +31243653102, Fax: +31243652190

Recently, we have observed ultrafast and nonthermal effects of light on magnetization. It was shown that a fs circularly polarized laser pulse acts on spins as a similarly short magnetic field pulse with strengths up to 1 T. Moreover, excitation by right- and left-handed circularly polarized pulses corresponds to magnetic fields of opposite polarity. Therefore, in contrast to the well-known magneto-optical Faraday effect, where the polarization of light is affected by magnetic order, these experiments demonstrate the feasibility of the inverse, opto-magnetic phenomenon: polarized light affects magnetic order via the inverse Faraday effect. Such laser-generated magnetic field is a fundamentally novel stimulus of magnetism providing unprecedented means for excitation and coherent control of spins on a subpicosecond timescale.

#### ACKNOWLEDGEMENTS

This work was partially supported by the European IST network SPINOSA, the RTN network DYNAMICS, the Russian Foundation for Basic Research (RFBR), Nederlandse Organisatie voor Wetenschappelijk Onderzoek (NWO), the Dutch NanoNed as well as Stichting voor Fundamenteel Onderzoek der Materie (FOM)

#### REFERENCES

- [1] A. V. Kimel, A. Kirilyuk, A. A. Tsvetkov, R. V. Pisarev and Th. Rasing, Laser-induced ultrafast spin reorientation in the antiferromagnet  $\text{ThFeO}_3$ , *Nature* 49, 850 (2004).
- [2] A. V. Kimel, A. Kirilyuk, P. A. Usachev, R. V. Pisarev, A. M. Balbashov, R. V. Pisarev, and Th. Rasing, "Ultrafast non-thermal control of magnetization by instantaneous photomagnetic pulses", *Nature* 435, 655 (2005).
- [3] F. Hansteen, A. V. Kimeel, A. Kirilyuk, and Th. Rasing, Femtosecond photomagnetic switching of spins in ferrimagnetic garnet films, *Phys. Rev. Lett.* 95, 047402 (2005).
- [4] F. Hansteen, A. V. Kimeel, A. Kirilyuk, and Th. Rasing, Nonthermal ultrafast optical control of the magnetization in garnet films, *Phys. Rev. B* 73, 014421 (2006).

FB01

### Extraordinary Magnetoresistance Effects and Local Control of Magnetocrystalline Anisotropy in $(\text{Ga},\text{Mn})\text{As}$ Devices

J. Wunderlich<sup>1</sup>, T. Jungwirth<sup>1,3</sup>, A. C. Irvine<sup>4</sup>, A. B. Shick<sup>2</sup>, J. Zemen<sup>2</sup>, A. W. Rushforth<sup>1</sup>, C. T. Foxon<sup>3</sup>, R. P. Campion<sup>3</sup>, D. A. Williams<sup>1</sup> and B. Gallagher<sup>3</sup>

<sup>1</sup>Hitachi Cambridge Laboratory, Cambridge CB3 0HE, United Kingdom  
<sup>2</sup>Institute of Physics ASCR, Cukrovarnická 10, 162 53 Praha 6, Czech Republic  
<sup>3</sup>School of Physics and Astronomy, University of Nottingham, Nottingham NG7 2RD, United Kingdom  
<sup>4</sup>Microelectronics Research Centre, University of Cambridge, CB3 0HE, United Kingdom  
\*Corresponding author: jw526@cam.ac.uk, Phone: +44 1223 442901, Fax: +44 1223 467942

The family of  $(\text{III},\text{Mn})\text{V}$  ferromagnetic semiconductors offers unique opportunities for exploring the integration of two frontier areas in information technology: spintronics and nano-electronics.

In my talk I will address two novel phenomena recently observed in micro- and nano-structures patterned from this ferromagnetic material with strong spin-orbit coupling, the Coulomb blockade Anisotropic Magnetoresistance (CBAMR) [1] effect and lithographically controlled magnetocrystalline anisotropy applied for current induced domain wall propagation [2]. I will first address the CBAMR effect in a  $(\text{Ga}, \text{Mn})\text{As}$  single electron transistor. We found low-field hysteretic magnetoresistance which can exceed 3 orders of magnitude. The sign and size of the magnetoresistance signal are controlled by the gate voltage.




Fig. 1. (a) Schematics of our ferromagnetic SET. Trench isolated side-gate and channel aligned along the  $[110]$  direction were patterned by e-beam-lithography and reactive ion etching in a 5 nm  $(\text{Ga}_{0.998}\text{Mn}_{0.002})\text{As}$  epilayer. (b) CB conductance  $(I/V)$  oscillations with gate voltage for different source-drain bias. The diamond patterns in this 2D plot are clear fingerprints of single-electron transport.

The CBAMR is interpreted in terms of electrochemical shifts associated with magnetization rotations. Effective kinetic-exchange model calculations in  $(\text{Ga},\text{Mn})\text{As}$  show chemical potential anisotropies consistent with experiment and ab-initio calculations in transition metal systems suggest that this generic effect persists to high temperatures in metal ferromagnets with strong spin-orbit coupling.

In the second part I will present recent experiments and theoretical modeling for lithographically engineered crystalline anisotropy in  $(\text{Ga},\text{Mn})\text{As}$  microdevices. The utility of locally controlled magnetic anisotropies is demonstrated in current induced switching experiments. We observed current induced magnetization switchings by domain wall propagation well below the Curie temperature at critical current densities  $\sim 10^8 \text{ A/cm}^2$ .

#### REFERENCES

- [1] J. Wunderlich et al. *Phys. Rev. Lett.* 97, 077201 (2006)
- [2] J. Wunderlich et al. submitted to *Phys. Rev. Lett.* S. Huempfer, et al. (2006), cond-mat/0612439. K. Pappert, et al. (2007), cond-mat/0701478; J. Wemisch, et al., (2007), cond-mat/0701479.