79

오배자 추출 폴리페놀류 처리 면섬유의 항산화성 분석 Evaluation of Anti-oxidant Activity of Cotton fabrics treated with the Gallnut Extracts

장경진, 손송이, 정종석¹, 김태경

경북대학교 공과대학 섬유시스템공학과, ¹경북대학교 기능물질공학과

Abstract

In order to introduce new functions onto textile fabrics, cotton was treated with gallnut extracts. And then the anti-oxidant activity of fabrics treated with the extracts was evaluated by Blois method using DPPH $(\alpha,\alpha-diphenyl-\beta-picrylhydrazyl)$. The anti-oxidant activity was exhibited on the textile fabrics treated as well as by the extracts itself.

1. 서 론

최근 들어 텍스타일 분야에 있어서도 여러 가지 기능성을 추구하는 고기능성 제품개발에 이어 웰빙 제품의 전개가 이루어지고 있다. 이러한 웰빙 제품의 전개에 있어서 독자적인 영역을 확보하고 있는 분야가 바로 천연 재료 및 천연기능성 물질을 활용한 텍스타일 제품 분야이며, 오배자 추출물에 의한 가공도 여기에 속한다고 할 수 있다. 오배자는 갈로탄닌류가 주성분이고 천연에서 쉽게 많은 양을 얻을 수 있고, 색상이 거의 없으며, 분말화 및 처리가 용이한 다양한 장점을 지닌다. 이러한 오배자 추출물을 이용하여 추출물 내 항산화 물질의 활성을 분석하였고, 직물에 처리한 후 직물의 기능성을 조사하였다.

2. 실 험

2.1 시료

실험에 중국산 오배자를 사용하였으며, 추출물로 처리한 직물소재는 KS K 0905 규격의 백면포를 사용하였다.

2.2 처리 및 분석

각 시료를 1:20 욕비에서 오배자 추출물 1~10 o.w.f.를 사용하여서 60℃에서 60분간 면직물에 처리

하였다. 추출물로 처리된 면직물의 활성 분석을 위해 총 폴리페놀 함량은 AOAC의 Folin-Denis법을 일부 변형하여 비색 정량하였고, 유효 항산화성(전자공여능)을 분석하기 위해 Blois의 법을 이용하여 평가하였다.

3. 결 론

Fig. 1은 다양한 농도의 추출물로 처리된 면직물의 폴리페놀 함량을 분석하기 위해 측정한 흡광도 그래프이다. Fig. 1의 그래프로 부터 유효 폴리페놀 함량을 계산하여 fig. 2에 그래프화 하였다. 그래프에서 알수 있듯이처리 농도가 증가함에 따라 직물이 포함하는 폴리페놀이 증가 하였다. Fig. 3는 추출물로 처리된 면직물의 항산화성을 측정하기 위해 DPPH 용액을 사용해 분석한 그래프로 추출물의 농도가 진해질수록 흡광패턴이 낮아짐을 볼 수 있다. Fig. 3의 결과로부터 오배자로 처리된 직물들의 항산화성을 계산할 수 있고이를 Fig. 4에 그래프화 하였다. Fig. 4를 보면 오배자 추출물의 농도가 증가함에 따라 항산성 역시 비례적으로 증가하는 것을 볼 수 있다. 이러한 결과는 폴리페놀과 같은 성분들을 포함하는 음식을 섭취하거나 피부에 바르는 것 외에 섬유에 의해서도 인체에 항산화성을 나타낼 수 있음을 의미한다.




Fig. 1. UV-VIS spectra of Folin reagent solution containing the cotton treated with gallnut extracts.




Fig. 3. UV-VIS spectra of DPPH solutions containing the cotton treated with gallnut extracts.




Fig. 2. Effective polyphenol content of the cotton treated with gallnut extracts.




Fig. 4. EDA (anti-oxidant activity) of the cotton treated with gallnut extracts.

Tel.: +82-11-9368-1699; e-mail: love29j@hanmail.net

80 _____www.ksdf.or.kr