

AS16

Magnetic Shielding Effectiveness Measurement of Magnetic Steel Sheets in ELF Range

Kyoheum Yeon¹, Derac Son^{1*}, Eon byeong Park², Jae Young Lee², Kyung Hwan Do³, and Jae Seg Park³

¹Department of Physics, Hannam University Ojung-dong 133 Daejeon, Korea

²Environment Research Center, RIST Hyoja-dong 32 Pohang, Korea

³Cold Rolled Product Technology Team, POSCO Center Daechi-dong 4 Seoul, Korea

*Corresponding author: Derac Son, e-mail: deracson@hnu.kr

Magnetic field shield becomes more important due to the not only EMI/EMC problems but also bad influence to the human body[1,2]. Many countries now

have regulation for magnetic field strength limit in ELF range. Magnetic Shielding Effectiveness (MSE) measuring method for constructions is in ASTM[3], but there is no measuring method for sheet specimen. In this work, we have designed new type of MSE measuring equipment for steel sheet specimens "biowave-steel" which is produced in POSCO. MSE measurement for steel sheet, we invoked two yokes. One is magnetizing yoke and the other is sensing yoke as shown in Fig. 1. And test specimen put into between two yokes. MSE was calculated from induced voltage of sensing yoke with sample V1 and without sample V2

$$MSE = \frac{V_2}{V_1} \quad (1)$$

For higher reproducible measurement, gaps between magnetizing yoke and specimen, and magnetizing yoke and sensing yoke were fixed 3 mm and 8 mm respectively. Fig. 2 shows the constructed yoke system. MSE measurement for the biowave-steel frequency ranging from 10 Hz to 10 kHz for different specimen size is shown in Fig. 3. We can see that MSE depends on the specimen size. When frequency is low, specimen size of 8 mm × 8 mm enough, but higher frequency we need specimen size of 140 mm × 140 mm, because of enough large specimen size for eddy current loop generation.

REFERENCES

- [1] J.L. Norman Violette, D.R.J. White, and M. F Violette, Electromagnetic Compatibility Handbook, Van Nostrand Reinhold Co. 1987.
- [2] K. Fitzgerald, "Electromagnetic fields: the jury's still out", IEEE spectrum Agust, pp. 22-35(1990).
- [3] ASTM A698M-92.




Fig. 1. Compose of magnetizing yoke and sensing yoke.




Fig. 2. The constructed yoke system.




Fig. 3. MSE measurement for the bio stel frequency ranging from 10Hz to 10kHz.

AS17

Cation Distribution and Magnetic Properties of the Spinel FeCr_{1.9}Al_{0.1}S₄

Chin Mo Kim¹, Bo Ra Myoung¹, Yong Hwan Bak², Sam Jin Kim¹, and Chul Sung Kim^{1*}

¹Department of Physics, Kookmin University, Seoul 136-702, Korea

²Sciences and Liberal Arts, Young dong University, Korea

*Corresponding author: Chul Sung Kim, e-mail: cskim@kookmin.ac.kr

The cation distribution and magnetic properties of FeCr_{1.9}Al_{0.1}S₄ were investigated using X-ray diffractometer (XRD), vibrating sample magnetometer (VSM) and Mössbauer spectroscopy measurement. The crystal structure is determined to be a cubic spinel with space group *Fd-3m* and the lattice constant is found to be $a_0 = 9.998 \text{ \AA}$.

The temperature dependence of magnetization was measured at various external fields. Fig. 1. shows the zero field cooled (ZFC) and field cooled (FC) curves under 100 Oe external field. The magnetization followed a Curie-weiss law with a positive Curie temperature $\theta_w = 160 \text{ K}$ showing ferrimagnetic behaviors. We have observed the large irreversibility in ZFC and FC curves, at low external magnetic field. It disappeared gradually with increasing external field. It shows a cusp shape at 68 K which is explained by the magnetic domain motion. Moreover a weak kink at 100 K is observed in which magnetization decrease with increasing temperature and then it abruptly increase again. This abnormal feature is interpreted by magnetic fluctuation as substituting non magnetic ion Al³⁺ in the octahedral (B) site.




Fig. 1. The temperature dependence of zero-field-cooled and field-cooled magnetization for FeCr_{1.9}Al_{0.1}S₄ under the 100 Oe external field.