

Undoped ZnO 박막의 다양한 특성의 상관관계에 대한 연구

A study on the relationship of various characterizations for undoped ZnO thin films

백경현¹, 박형식¹, 장경수¹, 정성욱¹, 유경열¹, 윤의중², 이준신^{1,*}

Kyung Hyun Baek, Hyeongsik Park, Kyung soo Jang, Sung Wook Jung, kyungyul Ryu, Eui Jung Yun and J. Yi

¹성균관대학교, ²호서대학교

Sungkyunkwan University, ²Hoseo University

Abstract : PTC Thermistors specimens were fabricated by added MnO₂ as donors, and Nb₂O₅ as acceptors and sintered 1250°C/2hrs. Average grain size decreased with increased in added MnO₂, and increased with added in Nb₂O₅. But, appeared liquid phase as Bi₂O₃ and TiO₂, affect to grain growth. XRD result, peak strength waslowed then crystallization not well, but, secondary phase were not showed all specimens. All specimens resistance were so high, about 40MΩ over, couldn't measured to those resistance and doesn't appear PTCR effect.

Key Words : ZnO, Oxygen fraction, p-type, FE-SEM, XRD

1. 서 론

Hexagonal 구조를 가진 ZnO는 전도성이 우수하면서 투명한 물질로서 연구가 활발히 진행되고 있다. 특히나 II-VI족 화합물 반도체인 ZnO는 n-type 형태로 존재하는 물질이지만 p-type의 특성을 가진 ZnO를 만들기는 어렵다. 그래서 O₂ fraction 변화에 따라서 증착된 ZnO 박막을 고온 열처리를 통해 p-type ZnO 형성 여부와 안정화가 될 수 있는지에 대해 연구하였다. 하지만 undoped ZnO의 p-type 안정화에 대한 박막의 결정구조, 광학적 그리고 전기적 특성에 대한 상관관계가 정립되어 있지 않고 있으며 체계화 되어 있지 않는 실정이다. 그래서 이번 논문에서는 Undoped ZnO를 산소 열처리를 통해 시간 및 온도의 변화를 주면서 다양한 특성을 확인하고 이를 체계적으로 분석하였다.

2. 결과 및 토의

Undoped ZnO의 박막은 2θ의 값이 34.25°로 hexagonal wurzite 결정구조를 갖고 있는데 이는 ZnO 박막이 수직으로 C축 배향을 알 수 있다. 그리고 산소 분위기에서 어닐링 온도를 600°C로 고정하고 어닐링 시간에 따라서는 시간에 관계없이 박막 내에서의 스트레스가 작으며 이는 기존 Bulk ZnO의 d-value와 비교한 것을 통해서 알 수 있다.

그리고 열처리 온도가 증가하면서 비저항과 이동은 감소하나 전자농도는 증가하는 경향을 확인할 수 있는데 UV intensity 변화와는 큰 상관관계가 없을 보여주고 있는데 ZnO 격자구조로부터 O 원자의 지속적인 유출을 뒷받침하고 있다고 할 수 있으며 이는 열에너지에 의한 O원자의 지속적인 손실이 defect 농도를 증가시켜 전기적인 특성에 영향을 주는 것으로 볼 수 있다.

감사의 글

이 연구(논문)는 지식경제부의 지식경제 프론티어기술개발사업인 차세대정보디스플레이기술개발사업단의 연구비(과제번호 F0004062-2009-32)지원으로 수행되었습니다.

참고 문헌

[1] H. S. Kang, G. H. Kim, S. H. Lim, H. W. Chang, J. H. Kim and S. Y. Lee, Thin Solid Films 516 3147 2008.

† 교신저자) 이준신, e-mail: yi@yurim.skku.ac.kr, Tel: 031-290-7139
주소: 경기도 수원시 장안구 권천동 300 성균관대학교 전기전자정보통신공학부