

TM-P003

Optical Gap Bowing and Phonon Modes of Amorphous Ge_{1-x-y}SexAs_y Thin Films

소현섭¹, 박준우¹, 정대호¹, 이호선¹, 신혜영², 윤석현²,
안형우³, 김수동³, 이수연³, 정두석³, 정병기³

경희대학교 응용물리학과¹, 이화여자대학교 물리학과², 한국과학기술연구원 미래융합기술연구본부³

We investigated the optical properties of Ge_{1-x}Sex and Ge_{1-x-y}SexAs_y amorphous semiconductor films using spectroscopic ellipsometry and Raman spectroscopy. The dielectric functions and absorption coefficients of the amorphous films were determined from the measured ellipsometric angles. We obtained the optical gap energies and Urbach energies from the absorption coefficients, and found a strong bowing effect in the optical gap energy of Ge_{1-x-y}SexAs_y where the endpoint binaries were Ge_{0.50}Se_{0.50} and Ge_{0.31}As_{0.69}. Based on the correlation between optical gap energies and Urbach energies, the large bowing parameter was attributed to the electronic disorder. We found the composition dependence of several phonon modes using Raman spectroscopy. For Ge_{1-x-y}SexAs_y, the D mode (232-267 cm⁻¹) changed from As-As (or As₃ pyramid), to As(Se_{1/2})₃ pyramid, and finally to Se clusters, as the Se composition increased. Resonant Raman phenomenon was observed in Ge_{0.38}Se_{0.62} at a laser excitation of 514 nm (2.41 eV). We verified that this laser energy corresponds to the transition energy of Ge_{0.38}Se_{0.62} using the second derivative of the dielectric function of Ge_{0.38}Se_{0.62}.

Keywords: Ge_{1-x-y}SexAs_y, amorphous films, dielectric function, band gap, Urbach energy, phonon

TM-P004

Optical Emission Anisotropy in InP Aligned Quantum Dots

Y. H. Shin¹, Yongmin Kim¹, J. D. Song², Subong Choi³

¹Department of Applied Physics and Institute of Nanoscience and Biotechnology, Dankook University,

²Korea Institute of Science and Technology, ³Department of Physics, Incheon University

InP quantum dots were grown by using the molecular beam epitaxy technique. Quantum dots are connected and composed string-like one-dimensional structure due to the strain field along [110] crystal direction. Two prominent photoluminescence transitions from normal quantum dots and string-like one-dimensional structure were observed which show strong optical anisotropy along [1-10] and [110] crystal directions. Both peaks also showed blue-shift while rotating emission polarization from [1-10] to [110] direction. Such optical transition behaviors are the consequence of the valence band mixing caused by strain field along the [110] crystal direction.

Keywords: InP, Quantum dot, photoluminescence