

Dependence of Light-Emitting Characteristics of Blue Phosphorescent Organic Light-Emitting Diodes on Electron Injection and Transport Materials

Jeong-Ik Lee, Jonghee Lee, Joo-Won Lee, Doo-Hee Cho, Jin-Wook Shin,
Jun-Han Han, and Hye Yong Chu

We investigate the light-emitting performances of blue phosphorescent organic light-emitting diodes (PHOLEDs) with three different electron injection and transport materials, that is, bathocuproine(2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline) (Bphen), 1,3,5-tri(m-pyrid-3-yl-phenyl)benzene (Tm3PyPB), and 2,6-bis(3-(carbazol-9-yl)phenyl)pyridine (26DCzPPy), which are partially doped with cesium metal. We find that the device characteristics are very dependent on the nature of the introduced electron injection layer (EIL) and electron transporting layer (ETL). When the appropriate EIL and ETL are combined, the peak external quantum efficiency and peak power efficiency improve up to 20.7% and 45.6 lm/W, respectively. Moreover, this blue PHOLED even maintains high external quantum efficiency of 19.6% and 16.9% at a luminance of 1,000 cd/m² and 10,000 cd/m², respectively.

Keywords: Organic light-emitting diodes (OLED), blue, phosphorescent, electron transporting material, cesium, doping.

Manuscript received Jan. 17, 2012; revised May 8, 2012; accepted May 16, 2012.

This work was supported by IT R&D program of MKE/KEIT (10039141, Development of core technologies for organic materials applicable to OLED lightings with high color rendering index).

Jeong-Ik Lee (phone: +82 42 860 1166, jiklee@etri.re.kr), Jonghee Lee (clrpaper@gmail.com), Joo-Won Lee (spduck@hanmail.net), Doo-Hee Cho (chodh@etri.re.kr), Jin-Wook Shin (shinjw@etri.re.kr), Jun-Han Han (junhan@etri.re.kr), and Hye Yong Chu (hychu@etri.re.kr) are with the Convergence Components & Materials Research Laboratory, ETRI, Daejeon, Rep. of Korea.

<http://dx.doi.org/10.4218/etrij.12.0112.0014>

I. Introduction

Phosphorescent organic light-emitting diodes (PHOLEDs) are promising and tunable solid-state lighting sources for both lighting and display applications owing to their high light-emitting performances [1]-[5]. In particular, white organic light-emitting diodes (OLEDs) have been attractive candidates for future solid-state lighting sources since their power efficiencies have surpassed those of incandescent bulbs [1]-[3]. However, the light-emitting efficiency of blue PHOLEDs is much lower than their longer wavelength counterparts (such as green, orange, and red), thus restricting the performance of white PHOLEDs [6], [7]. In pursuing highly efficient blue PHOLEDs, various results have been demonstrated through the development of host materials and device structures [8]-[20]. Many types of device engineering, such as a mixed host, stepwise doping, or double emissive layer structure, have been reported to be applicable to blue PHOLEDs [8]-[14].

Enhanced blue PHOLED performances achieved through the development of carbazole-, trizine-, pridine-, or phenylsilane-type wide band-gap materials have also been reported [15]-[20]. Triplet exciton confinement in the emissive layer (EML) of PHOLEDs has been known as one of the key factors affecting the device characteristics [14], [18], [21], [22]. Since the blue electro-phosphorescent dopants have high triplet energy (T_1) levels, wideband gap hole transporting materials and electron transporting materials with high T_1 levels are required [12]-[14], [23]-[26]. Recently, Zheng and others found that the use of a hole transporting layer (HTL) with T_1 levels

improved the light-emitting performances of an iridium(III) bis(2,4-difluorophenylpyridinato)tetrakis(1-pyrazolyl)borate (FIr6) doped blue PHOLED with 1,4-Bis(triphenylsilyl)benzene (UGH2) as the host [23]. Their study resulted in 1,1-bis[(di-4-tolylamino)phenyl]cyclohexane (TAPC) ($T_1 = 2.87$ eV) giving a better exciton confinement compared to that of devices made with bis(*N*-(1-naphthyl)-*N*-phenylamino)biphenyl (NPB) ($T_1 = 2.29$ eV). However, there have been few systematic studies of the effect of the electron transporting layer (ETL) on the device characteristics.

In this work, we fabricate five blue PHOLEDs based on iridium(III)bis(4,6-difluorophenyl)-pyridinato-*N,C*² picolinate (FIrpic) with different combinations of electron injection materials and transport materials. We demonstrate that light-emitting characteristics such as current density, turn-on voltage, and performance are correlated with the energy level as well as the triplet energy of the introduced electron injection layer (EIL) and ETL.

II. Experiment

Five blue PHOLEDs (Devices A through E) are fabricated using a configuration of indium tin oxide (ITO)/TAPC (50 nm)/4,4',4''-tris(*N*-carbazolyl)triphenylamine (TcTa):FIrpic (7%, 10 nm)/2,6-bis(3-(carbazol-9-yl)phenyl)pyridine (26DCzPPy):FIrpic (20%, 10 nm)/ETL (x nm)/EIL (50- x nm)/LiF (1 nm)/Al (120 nm), as shown in Fig 1. TAPC with a wider triplet energy level (T_1) of 2.9 eV, which is higher than that of FIrpic ($T_1 = 2.62$ eV), and with a high-lying of the lowest unoccupied molecular orbital (LUMO) energy level, is used as the HTL/electron blocking layer [24]-[26]. As a standard device, a cesium (Cs) non-doped device with Bphen material (Device A) is prepared. A non-doped Bphen, Tm3PyPB, or 26DCzPPy layer is used as an ETL/hole blocking layer, the thickness of which is x nm with x varying from 20 to 50. Cesium doped into the ETL material is used as the n-type EIL, the thickness of which is (50- x) nm (Devices B through E). As the EML, we employ a double EML (D-EML) structure using TcTa and 26DCzPPy for the host materials of FIrpic in the two adjacent EMLs [8], [9]. The chemical structures of the materials and energy level diagrams used in this study are shown in Fig. 2 (the energy levels are taken from the literature).

ITO is cleaned using a standard oxygen plasma treatment. The OLED grade materials are purchased and used without further purification. All organic layers are deposited in a high-vacuum chamber below 5×10^{-7} torr, and thin LiF and Al films are deposited as a cathode electrode. The OLEDs are transferred directly from a vacuum into an inert environment glove-box, where they are encapsulated using a UV-curable epoxy and a glass cap with a moisture getter. The




Fig. 1. Device structures of blue PHOLEDs tested in this study.




Fig. 2. Chemical structures and energy level diagrams for materials tested in this study.

electroluminescence (EL) spectrum is measured using a Minolta CS-1000. The current density-voltage (J-V) and luminescence-voltage (L-V) characteristics are measured using a current/voltage source/measure unit (Keithley 238) and a Minolta CS-100, respectively.

III. Results and Discussion

The EL spectra of the blue PHOLEDs (Devices A through E) are shown in Fig. 3 according to the EIL and ETL materials. All devices exhibit a similar maximum luminescence wavelength at a driving current of 10 mA/cm², near 470 nm,




Fig. 3. Normalized EL spectra of Devices A through E at driving current of $10 \text{ mA}/\text{cm}^2$.

which originates from the triplet emission of FIripic dopant and the second vibration peaks with a wavelength of approximately 500 nm. The slight differences in the relative intensities of the second vibration peaks can be understood by the slight shift of the recombination zone as well as the different optical properties of the ETL/EIL combination [25]-[27].

Figure 4 shows the current density-voltage-luminance (J-V-L) curves of the blue PHOLEDs (Devices A through E) according to the EIL and ETL materials. We can easily see that the different combinations of ETL and EIL greatly influence the I-V-L characteristics of the blue PHOLEDs. Compared to standard Device A with only Bphen as the ETL/EIL, Device B with Cs doped Bphen as the EIL shows an increased current density as well as luminance at the same voltage. For example, the current density and luminance at a driving voltage of 4.5 V shows $8.5 \text{ mA}/\text{cm}^2$ (Device A) and $25.8 \text{ mA}/\text{cm}^2$ (Device B) and $1544 \text{ cd}/\text{m}^2$ (Device A) and $5699 \text{ cd}/\text{m}^2$ (Device B), respectively. This could be attributed to the difference in the electrical conductivity of the Cs doped Bphen as the EIL, which results in a reduction of the total resistance of the organic layers and an enhancement of the charge injection from the electrode [11], [25], [28].

In terms of the external quantum efficiency (EQE) characteristics, Device B shows a slight increase compared to standard Device A; however, this increase is not impressive due to the lower T_1 of Bphen (2.5 eV) compared to that of FIripic (2.65 eV) [25]. In Fig. 5, the EQE characteristics of blue PHOLEDs are plotted against the current density. To overcome the low efficiency of Device B, we fabricate Devices C and D, which have wider T_1 materials (Tm3PyPB and 26DCzPPy) as ETL/EIL, along with Cs doping. To achieve efficient blue PHOLEDs, an effective confinement of the triplet exciton is necessary [10], [14], [17]. Since the triplet energy level of both Tm3PyPB and 26DCzPPy ($T_1 = 2.78 \text{ eV}$ and 2.71 eV ,




Fig. 4. (a) Current density-voltage (J-V) and (b) luminescence-voltage (L-V) characteristics of Devices A through E.

respectively) is higher than that of FIripic, the triplet exciton of FIripic can be confined within the EML. Accordingly, we find highly enhanced EQEs in Devices C and D, as shown in Fig. 5. The peak EQEs of Devices C and D are 20.7% and 21.5%, respectively, while those of Devices A and B are only 10.1% and 12.1%.

Moreover, these enhanced EQEs that are a 1.9-fold enhancement compared with that of Device B with Bphen (18.7 lm/W) of around $100 \text{ cd}/\text{m}^2$, along with reduced driving voltages, result in a significantly increased maximum luminance efficiency (LE) of 36.7 lm/W (Device C with Tm3PyPB) and 35.8 lm/W (Device D with 26DCzPPy) without an out-coupling enhancement technique. In Fig. 6, the LE characteristics of the blue PHOLEDs are plotted against brightness.

To obtain higher LE, especially for lighting applications with OLED technology, a low driving voltage is necessary. Note that the turn-on voltage of Device D is 0.5 V lower than that of Device C, which can be explained by a lower electron injection




Fig. 5. EQE vs. current density characteristics of Devices A through E.




Fig. 6. LE vs. brightness characteristics of Devices A through E.

barrier from the ETL to the EML. The LUMO levels of 26DCzPPy and Tm3PyPB are 2.56 eV and 2.78 eV, respectively. Thus, Device C with Tm3PyPB encounters an additional electron injection barrier (0.22 eV), which causes an increased driving voltage compared with that of Device D. However, there is another aspect to consider in terms of the current density slope at the light-emitting region. Even though the driving voltage of Device D is lower than that of Device C, the current density slope of Device C is much steeper than that of Device D, as Tm3PyPB has a much higher electron mobility and an adequate HOMO level for hole blocking than does 26DCzPPy. For instance, the current density of Device C at a driving voltage of 6.0 V shows 69.6 mA/cm², while that of Device D is only 29.2 mA/cm². By combining the advantages of Device C (steep current density slope) and Device D (low driving voltage), we fabricate Device E, which is constituted by 26DCzPPy ETL and Cs doped Tm3PyPB EIL. As a result, we develop a highly efficient blue PHOLED, which shows a low driving voltage as well as a steep increase of the current density.

Consequently, the maximum LE of Device E reaches up to 45.6 lm/W and can be expected to be over 100 lm/W, considering the potential of the improved out-coupling technique to achieve a 2.3-fold enhancement [1], [3], [25].

IV. Conclusion

Investigating the nature of a Cs-doped ETL, we successfully developed highly efficient blue PHOLEDs along with a reduced driving voltage and an enhanced quantum efficiency, in which a peak power efficiency of 45.6 lm/W without an out-coupling enhancement was shown.

References

- [1] L. Xiao et al., "Recent Progresses on Materials for Electrophosphorescent Organic Light-Emitting Devices," *Adv. Mater.*, vol. 23, 2011, pp. 926-952.
- [2] K.T. Kamtekar, A.P. Monkman, and M.R. Bryce, "Recent Advances in White Organic Light-Emitting Materials and Devices (WOLEDs)," *Adv. Mater.*, vol. 22, 2010, pp. 572-582.
- [3] S. Reineke et al., "White Organic Light-Emitting Diodes with Fluorescent Tube Efficiency," *Nature*, vol. 459, 2009, pp. 234-238.
- [4] J.Y. Lee, J.H. Kwon, and H.K. Chung, "High Efficiency and Low Power Consumption in Active Matrix Organic Light Emitting Diodes," *Org. Electron.*, vol. 4, 2003, pp. 143-148.
- [5] J. Lee et al., "Interlayer Engineering with Different Host Material Properties in Blue Phosphorescent Organic Light-Emitting Diodes," *ETRI J.*, vol. 33, 2011, pp. 32-38.
- [6] C. Adachi et al., "Nearly 100% Internal Phosphorescence Efficiency in an Organic Light-Emitting Device," *J. Appl. Phys.*, vol. 90, 2001, pp. 5048-5051.
- [7] D. Tanaka et al., "Ultra High Efficiency Green Organic Light-Emitting Devices," *Jpn. J. Appl. Phys.*, vol. 46, 2007, pp. L10-L12.
- [8] S.J. Su et al., "Highly Efficient Organic Blue- and White-Light-Emitting Devices Having a Carrier- and Exciton-Confining Structure for Reduced Efficiency Roll-Off," *Adv. Mater.*, vol. 20, 2008, pp. 4189-4194.
- [9] J. Lee, J.I. Lee, and H.Y. Chu, "Investigation of Double Emissive Layer Structures on Phosphorescent Blue Organic Light-Emitting Diodes," *Synth. Met.*, vol. 159, 2009, pp. 1460-1463.
- [10] J. Lee et al., "Influence of Doping Profile on the Efficiency of Blue Phosphorescent Organic Light-Emitting Diodes," *Appl. Phys. Lett.*, vol. 92, 2008, 133304.
- [11] S.H. Eom et al., "Low Voltage and Very High Efficiency Deep-Blue Phosphorescent Organic Light-Emitting Devices," *Appl. Phys. Lett.*, vol. 93, 2008, 133309.
- [12] J. Lee et al., "Enhanced Efficiency and Reduced Roll-Off in Blue

- and White Phosphorescent Organic Light-Emitting Diodes with a Mixed Host Structure," *Appl. Phys. Lett.*, vol. 94, 2009, 193305.
- [13] J. Lee et al., "Improved Performance of Blue Phosphorescent Organic Light-Emitting Diodes with a Mixed Host System," *Appl. Phys. Lett.*, vol. 95, 2009, 253304.
- [14] J. Lee et al., "Effects of Interlayers on Phosphorescent Blue Organic Light-Emitting Diodes," *Appl. Phys. Lett.*, vol. 92, 2008, 203305.
- [15] C. Adachi et al., "Endothermic Energy Transfer: A Mechanism for Generating Very Efficient High-Energy Phosphorescent Emission in Organic Materials," *Appl. Phys. Lett.*, vol. 79, 2001, pp. 2082-2084.
- [16] H. Inomata et al., "High-Efficiency Organic Electrophosphorescent Diodes Using 1,3,5-Triazine Electron Transport Materials," *Chem. Mater.*, vol. 16, 2004, pp. 1285-1291.
- [17] S.J. Su et al., "Wide-Energy-Gap Electron-Transport Materials Containing 3,5-Dipyridylphenyl Moieties for an Ultra High Efficiency Blue Organic Light-Emitting Device," *Chem. Mater.*, vol. 20, 2008, pp. 5951-5953.
- [18] R.J. Holmes et al., "Efficient, Deep-Blue Organic Electrophosphorescence by Guest Charge Trapping," *Appl. Phys. Lett.*, vol. 83, 2003, pp. 3818-3820.
- [19] M.H. Tsai et al., "Triphenylsilyl- and Trityl-Substituted Carbazole-Based Host Materials for Blue Electrophosphorescence," *ACS Appl. Mater. Interfaces*, vol. 1, 2009, pp. 567-574.
- [20] J.J. Lin et al., "A Highly Efficient Host/Dopant Combination for Blue Organic Electrophosphorescence Devices," *Adv. Funct. Mater.*, vol. 18, 2008, pp. 485-491.
- [21] Y. Kawamura et al., "Intermolecular Interaction and a Concentration-Quenching Mechanism of Phosphorescent Ir(III) Complexes in a Solid Film," *Phys. Rev. Lett.*, vol. 96, Jan. 2006, 017404.
- [22] J. Lee et al., "Efficient White Phosphorescent Organic Light-emitting Diodes for Solid-State Lighting Applications Using an Exciton-confining Emissive-Layer Structure," *J. Info. Display*, vol. 10, 2009, pp. 92-95.
- [23] J. Lee et al., "Effects of Triplet Energies and Transporting Properties of Carrier Transporting Materials on Blue Phosphorescent Organic Light Emitting Devices," *Appl. Phys. Lett.*, vol. 93, 2008, 123306.
- [24] Y. Zheng et al., "Efficient Deep-Blue Phosphorescent Organic Light-Emitting Device with Improved Electron and Exciton Confinement," *Appl. Phys. Lett.*, vol. 92, 2008, 223301.
- [25] S.-H. Eom et al., "Effect of Electron Injection and Transport Materials on Efficiency of Deep-Blue Phosphorescent Organic Light-Emitting Devices," *Org. Electron.*, vol. 10, 2009, pp. 686-691.
- [26] J. Lee et al., "Stable Efficiency Roll-off in Blue Phosphorescent Organic Light-Emitting Diodes by Host Layer Engineering," *Org. Electron.*, vol. 10, 2009, pp. 1529-1533.
- [27] J. Lee et al., "Effects of Charge Balance on Device Performances in Deep Blue Phosphorescent Organic Light-Emitting Diodes," *Org. Electron.*, vol. 11, 2010, pp. 1159-1164.
- [28] K. Walzer et al., "Highly Efficient Organic Devices Based on Electrically Doped Transport Layers," *Chem. Rev.*, vol. 107, 2007, pp. 1233-1271.



Jeong-Ik Lee received his BS, MS, and PhD in chemistry from the Korea Advanced Institute of Science and Technology (KAIST), Daejeon, Rep. of Korea, in 1992, 1994, and 1997, respectively. After graduating, he joined the IBM Almaden Research Center, San Jose, CA, USA, as a post-doc, where he worked on organic light-emitting materials. He moved to ETRI, Daejeon, Rep. of Korea, in 1999 and has been continuing his research on organic light-emitting materials and devices.



Jonghee Lee received his BS, MS, and PhD in chemistry from the Korea Advanced Institute of Science and Technology (KAIST), Daejeon, Rep. of Korea, in 2002, 2004, and 2007, respectively. During his graduate period, he conducted research on conjugated polymers and related organic semiconductor devices. He joined ETRI, Daejeon, Rep. of Korea, in 2007 and has worked on white organic light-emitting diodes (WOLEDs) for display and lighting applications. Currently, he is working at the Institut für Angewandte Photophysik (IAPP) at the Technische Universität Dresden in Germany.



Joo-Won Lee received his MS and PhD in physics from Kyung Hee University, Seoul, Rep. of Korea, in 2003 and 2006, respectively. After graduating, he joined the Department of Materials Engineering at Auburn University, Auburn, Alabama, USA, as a post-doc. He moved to ETRI, Daejeon, Rep. of Korea, in 2008 and has been continuing his research on transparent organic light-emitting devices and light extraction techniques. Currently, he is working at Samsung Display Corporation.



Doo-Hee Cho received his PhD in materials chemistry from Kyoto University, Kyoto, Japan, in 1996. He worked in the areas of float glass and low-e coating at the glass research center of the KCC Corp. from 1996 to 1998. Since he joined ETRI, Daejeon, Rep. of Korea, in 1998, he has been involved in specialty optical fiber, transparent oxide TFT, and OLED lighting research. His major research interests include optical structure and light extraction of OLED. He has been working on international standardization for OLED lighting as a member of IEC TC34 since 2009.



Jin-Wook Shin received his BS from the Department of Electronic Engineering at Myongji University, Yongin, Rep. of Korea, in 2007 and his MS from the Department of Electronic Materials Engineering at Kwangwoon University, Seoul, Rep. of Korea. He joined ETRI, Daejeon, Rep. of Korea, in 2009. His current research interests include light extraction technologies for organic light-emitting devices.



Jun-Han Han received his BS and MS in electronic engineering from Hanyang University, Seoul, Rep. of Korea, in 2007 and 2009, respectively. He joined ETRI, Daejeon, Rep. of Korea, in 2009 and has been continuing his research on organic light-emitting diode lighting applications and next generation display.



Hye Yong Chu received her BS and MS in physics from Kyung Hee University, Seoul, Rep. of Korea, in 1987 and 1989, respectively. She joined ETRI, Daejeon, Rep. of Korea, in 1989. She earned her PhD in information display from Kyung Hee University in 2008. Her current research interests include novel device architectures in organic light-emitting devices and next generation display.