



## 다자비교시험을 통한 화학혼화제 고형분량 시험법의 신뢰성 및 FT-IR 분석에 대한 효용성 평가

김진철<sup>1)\*</sup> · 유혁진<sup>2)</sup> · 김홍삼<sup>1)</sup> · 박고은<sup>1)</sup>

<sup>1)</sup>

<sup>2)</sup> SGS

### A Round Robin Study of Solid Content Test and Applicability Estimation of FT-IR Analysis for Chemical Admixtures

Jin-Cheol Kim,<sup>1)\*</sup> Hyeok-Jin Yoo,<sup>2)</sup> Hong-Sam Kim,<sup>1)</sup> and Ko-Eun Park<sup>1)</sup>

<sup>1)</sup>Korea Expressway Corporation 50-5, Sancheok, Dongtan, Hwaseong, Gyeonggi 18489, Rep. of Korea

<sup>2)</sup>SGS Korea Co., Ltd., Madu-ri, Songtan, Pyongtaek, Gyeonggi 18489, Rep. of Korea

**ABSTRACT** Acceptance criteria for chemical admixtures of cement concrete were investigated in domestic and international specifications. The reliability was verified for solid content test method of chemical admixture examined statistical analysis by round robin test. The applicability of FT-IR spectroscopy for qualitative measurement of multi-compound chemical admixtures verified. From solid content experimental results, outlier analysed using Cochran, Grubbs and Dickson's Q test. Repeatability and reproducibility standard deviation for solid content results showed 0.25 and 0.098% respectively according to KS A ISO 5725-2 procedure, it can be confirmed reliability of test methods. FT-IR spectrum of liquefied or oven-dried chemical admixtures condition showed big differences. It is needed that the FT-IR analysis is performed on dry material. However there's no difference with the applicability of FT-IR spectroscopy for multi-compound chemical admixtures. So the utility of method analysis could not identify.

**Keywords** : acceptance test, round robin test, reliability verification, repeatability and reproducibility standard deviation

### 1. 서 론

2560

가 . KS F

(ASTM C 494<sup>2)</sup>)

(uniformity and equivalence tests)

. KS F 2560<sup>1)</sup>

가

(EN 934<sup>3)</sup>)

가

가

(general requirements)

FHWA

AE

(foam drainage),

(foam index) 가

<sup>4)</sup>

KS A ISO

가

\*Corresponding author E-mail : jckim1213@naver.com

5725-2

Received July 16, 2015, Revised September 3, 2015,

Accepted September 3, 2015

(FT-IR)

## 2. 인수검사 시험기준 및 시험 개요

### 2.1 국내기준

2009-780 5)  
 KS F 2560  
 FT-IR  
 KS F 2560 FT-IR  
 3 가

가 ASTM C 494

6)  
 ±12% KS F 2560  
 ±10% A  
 ( ) KS F 2560  
 200 80%  
 2014

7)  
 EN 934-1 25%,  
 1.1 kg/L  
 ( Table 2 ).

### 2.2 국외기준

JIS A 6204<sup>9)</sup> 가  
 가  
 가  
 ( 1 / 3 , 1 / 1 ) 가  
 ( , , )  
 가

ASTM C 494

(Level I)

가 ,  
 가 (Level II) ,

가 ,  
 가 (Level III)

가  
 , AE , pH  
 가  
 EN 934-1  
 Table 1 , ,  
 pH, 가 11

AE

, , , pH  
 가 1 3 1,000 1  
 , ,  
 1 1

**Table 1** Guideline for acceptance testing of specifications

	Division	The main test method and evaluation item
JIS A 6204	1	• All items test
	2	• Water reducing ratio, slump, air, total chlorine, compressive strength etc.
ASTM C 494	I	• During the initial approval stage • Quality standards, all items and equivalence tests
	II	• Limited quality tests according to purchaser request • Quality standards, some of the items
	III	• Quality change test of import level • Equivalence tests (solid, density, pH, air etc)
EN 934-1	1	• Homogeneity
	2	• Colour
	3	• Effective component
	4	• Absolute density (for liquid admixtures only)
	5	• Conventional dry material content
	6	• pH value (for liquid admixtures only)
	7	• Total chlorine
	8	• Water soluble chlorine
	9	• Alkali content (Na <sub>2</sub> O equivalent)
	10	• Corrosion behaviour
	11	• Silicon dioxide SiO <sub>2</sub> content

**Table 2** Acceptance criteria for solid content and density of chemical admixtures

	Solid content	Absolute density
ASTM C 494	$0.88T \leq X \leq 1.12T$	$[_{adm} \times 10\%, [_{adm} - T_{water} \geq 0.01$ $[_{adm} \pm 0.01, [_{adm} - T_{water} < 0.01$
EN 934-1	$0.95T \leq X \leq 1.05T, T \geq 20\%$ $0.90T \leq X \leq 1.10T, T < 20\%$	$D \pm 0.03, D > 1.10\text{kg/l}$ $D \pm 0.02, D \leq 1.10\text{kg/l}$
Korea Expressway Corps.	$0.95T \leq X \leq 1.05T, T \geq 25\%$ $0.90T \leq X \leq 1.10T, T < 25\%$	$D \pm 0.03, D > 1.10\text{kg/l}$ $D \pm 0.02, D \leq 1.10\text{kg/l}$

Remark) T : standard value, X : test value,  
 $[_{adm}$  : density of admixture,  
 $[_{water}$  : distilled water of admixture  
 D : density of admixture

Table 2 ASTM C 494 EN 934

ASTM C 494	EN 934
$\pm 12\%$	$\pm 5\%, 20\%$
$\pm 10\%$	ASTM C 494
0.01	10%
, EN 934	1.1 kg/l
ASTM C 494	2010
934-1	2014

### 2.3 시험개요

2.3.1 고형분량 시험법의 신뢰성 검증  
 8)

3

( Semi-PC S-PC)  
 ( PC) 3  
 3  
 9 가 12  
 KS A ISO 5725-2  
 ( ) - 2 :  
 11)  
 3

#### 2.3.2 FT-IR 시험의 효용성 검증

FT-IR (Fourier transform infrared spectroscopy,  
 )

가  
 C 494 EN 934-1 , ASTM  
 C 494 18.1 EN 480-6 ASTM  
 KBr ,  
 가 ,  
 가 ,  
 KS F 2560  
 KS M 0024  
 3  
 가  
 , KS M 0024 FT-IR

가

FT-IR

2

FT-IR

### 3. 시험결과

#### 3.1 고형분량 시험법의 신뢰성 검증

3.1.1 고형분량 시험법 비교

Table 3

ASTM C 494 EN 480-8

KS Q ISO 13528-2009<sup>10)</sup>

ASTM C 494  
 (Ottawa , 20-30 mesh)  
 EN 480-8

4

KS M 0009


12

( LG),

ASTM C 494 EN 480-8

**Table 3** Quality standard of solid and density

	ASTM C 494	EN 480-8
Drying method	Standard sand method	Direct drying admixture
Drying time	17±1/4(h)	4(h)



**Fig. 1** Solid content test results

(LG) (PC)  
EN 480-8 가  
가  
ASTM C 494 5%  
ASTM C 494  
ASTM C 494

3.1.2 다자시험에 의한 고형분량 시험법의 신뢰성 검증

KS Q ISO 13528-2009  
5가  
9  
가  
2  
Table 4  
F-  
3, 5% F 가  
t- 4, 5%  
가  
9 12  
2  
5%  
Cochran Table 5  
Cochran 가

**Table 4** Homogeneity test results of reference materials

Classifications	LG(3)		Semi-PC(2)		PC(3)		
	No. 1	No. 2	No. 1	No. 2	No. 1	No. 2	
Test results(%)	37.86	37.92	19.03	18.45	21.05	21.32	
	37.89	37.90	18.47	18.83	21.35	21.44	
	37.86	37.92	19.15	19.10	20.91	21.11	
Average(%)	37.87	37.91	18.88	18.79	21.10	21.29	
Variance(%)	0.00	0.00	0.13	0.11	0.05	0.03	
F-Test	Numbers	3	3	3	3	3	
	Degree of freedom	2	2	2	2	2	
	F ratio	2.26	-	1.24	-	1.78	
	Critical value : One-tail	19	-	19	-	19	
T-test	Degree of freedom	4	-	4	-	4	
	t Value	-0.02	-	0.32	-	-1.15	
	Critical value	one-tail	2.13	-	2.13	-	2.13
		two-tail	2.78	-	2.78	-	2.78

**Table 5** Cochran test results

Types	LG			Semi-PC			PC		
	1	2	3	1	2	3	1	2	3
$s_{max}$	0.288	0.212	0.141	0.141	0.283	0.187	0.244	0.160	0.479
$\sqrt{s_i^2}$	0.110	0.075	0.070	0.047	0.075	0.090	0.087	0.041	0.279
Cochran value	0.756	0.597	0.286	0.426	1.061	0.389	0.683	0.620	0.823
C(2:0.05)	0.541	0.541	0.541	0.541	0.541	0.541	0.541	0.541	0.541
Judgement	N.G.	N.G.	O.K.	O.K.	N.G	O.K.	N.G.	N.G.	N.G.
error(%)	-2.0	1.3	-	-	0.4.	-	2.4	1.4	1.2

**Table 6** Grubbs test results

Types	LG			Semi-PC			PC		
	1	2	3	1	2	3	1	2	3
Min.	23.46	30.41	37.59	14.90	19.03	22.86	15.02	18.13	21.05
Max.	24.62	31.74	38.97	15.70	19.50	23.46	15.65	18.57	21.6
Average	24.12	31.18	38.23	15.33	19.32	23.19	15.38	18.36	21.31
s	0.344	0.371	0.400	0.213	0.157	0.208	0.174	0.129	0.152
$G_{min}$	1.919	2.075	1.600	2.019	1.847	1.587	2.069	1.783	1.711
$G_{max}$	1.453	1.509	1.850	1.737	1.146	1.298	1.552	1.628	1.908
G(n=12, 0.05p)				2.412					

$$C = \frac{s_{max}^2}{\sqrt{s_i^2}} \quad (1)$$

, C : Cochran's C statistic  
 $s_{max}$  : maximum standard deviation of data series  
 $s_i$  : standard deviation of data series

Cochran 가

LG 1, LG 2, PC1, PC2 PC 3

. KS A

ISO 5725-2

가

(

0.4~2.4%

Grubbs

12

2.412

5%

)

Table 2

ASTM

C 494

12%,

Grubbs

5 10%

가

, 가 Dixon Q

Table 7

가

Dixon's Q

12

Table 6

Grubbs

**Table 7** Dixon's Q-test results

Types	LG			Semi-PC			PC		
	1	2	3	1	2	3	1	2	3
Q <sub>exp(max)</sub>	0.248	0.332	0.828	0.272	0.289	0.361	0.242	0.387	0.353
Q <sub>exp(min)</sub>	0.153	0.196	0.124	0.229	0.106	0.205	0.225	0.170	0.082

12)

$$Q_{\text{exp(max)}} = \frac{x_n - x_{n-1}}{x_n - x_1} \quad (3)$$

$$Q_{\text{exp(min)}} = \frac{x_2 - x_1}{x_n - x_1} \quad (4)$$

, Q<sub>exp</sub>: Q-test statistics

x<sub>n</sub>: maximum value of data series

x<sub>n-1</sub>: closest value to maximum of data series

x<sub>2</sub>: closest value to minimum of data series

x<sub>1</sub>: minimum value of data series

95% , n=12 Q<sub>crit</sub> 0.426

(Q<sub>crit</sub>)

12

9

$$\hat{m}_j = \bar{y}_j = \frac{\sum_{i=1}^p n_{ij} y_{ij}}{\sum_{i=1}^p n_{ij}} \quad (5)$$

$$s_{rj}^2 = \frac{\sum_{i=1}^p (n_{ij} - 1) s_{ij}^2}{\sum_{i=1}^p (n_{ij} - 1)} \quad (6)$$

$$s_{Lj}^2 = \frac{s_{cj}^2 - s_{rj}^2}{n_j} \quad (7)$$

$$s_{cj}^2 = \frac{1}{p-1} \sum_{i=1}^p n_{ij} (\bar{y}_{ij} - \bar{y}_j)^2 = \frac{1}{p-1} \left[ \sum_{i=1}^p n_{ij} (\bar{y}_{ij})^2 - (\bar{y}_j)^2 \sum_{i=1}^p n_{ij} \right]$$

$$\bar{y}_j = \frac{1}{p-1} \left[ \sum_{i=1}^p n_{ij} - \frac{\sum_{i=1}^p n_{ij}^2}{\sum_{i=1}^p n_{ij}} \right] \quad (8)$$

s<sub>Lj</sub><sup>2</sup> 가 가 0

$$s_{Rj}^2 = s_{rj}^2 + s_{Lj}^2 \quad (9)$$

가 Table 8

2  
( ) 0.09% ,  
0.059~0.152% 1%  
가  
가 ( ) 0.25%  
0.14~0.40%  
0.74~1.45%

가 가

**Table 8** Repeatability and reproducibility standard deviation

Types	Level	Average( $\hat{m}_j$ )	S <sub>rj</sub> *	S <sub>Rj</sub> **
LG	1	24.12	0.096	0.350
	2	31.18	0.077	0.369
	3	38.23	0.076	0.404
PC(S)	1	15.33	0.063	0.218
	2	19.32	0.120	0.178
	3	23.19	0.087	0.217
PC	1	15.38	0.085	0.184
	2	18.36	0.059	0.136
	3	21.31	0.152	0.187
Average			0.090	0.249

Remark) \* : repeatability standard deviation(S<sub>rj</sub>)

\*\* : reproducibility standard deviation(S<sub>Rj</sub>)




Fig. 2 Dependency of repeatability standard deviation




Fig. 4 FT-IR peak analysis due to sample condition




Fig. 3 Dependency of reproducibility standard deviation

KBr  
 KBr  
 FT-IR  
 FT-IR  
 3,400 cm<sup>-1</sup>  
 가  
 가  
 가  
 Fig. 4  
 C-H 3,080,  
 C=O 1,730 COO<sup>-</sup> 1,575, 1,418 C-O 1,188, 1,043 cm<sup>-1</sup>  
 가  
 MPEG  
 (methoxy-polyethylene glycole)  
 2,930 cm<sup>-1</sup>  
 PEG C-H 가  
 3,400 cm<sup>-1</sup>

1 24.12%  
 가 가  
 95% ±0.58%

가 Fig. 2 3

가

### 3.2 FT-IR 적용성 평가

#### 3.2.1 액상 및 건조시료의 FT-IR 적용성 평가

FT-IR

ASTM C 494 18.1 EN 480-6

#### 3.2.2 혼합된 혼합제의 FT-IR 적용성 평가

KS F 2560

가

가

가

2

가

AE

AE

AE  
FT-IR  
AE  
0~5%  
5  
가  
가  
SLES (sodium lauryl ether sulfate)  
2,910, 2,850, 1,470, 1,210, 1,020  $\text{cm}^{-1}$

Fig. 5 AE  
5%  
가  
AE  
가  
가  
AE  
가  
가

AE  
가  
가  
가  
40%




Fig. 5 FT-IR analysis of PC, AE and PC+5% AE




Fig. 6 FT-IR analysis of PC, LG and PC+40%LG

FT-IR  
C-H  
2,960, C=C 1,590 C-C 1,420, 1,270, 1,192, 1,182,  
1,127, 1,050  $\text{cm}^{-1}$   
가  
S=O 가 1,170  
가 40%

Fig. 5  
가

FT-IR 2  
가

#### 4. 결 론

FT-IR  
1) 가  
ASTM C 494  
2) 12  
가 Cochran  
6  
가  
0.4~2.4%  
10%  
3) 가 Grubbs  
Dixon Q 가  
KS A ISO 5725-2  
12  
0.09 0.249%  
4) FT-IR 가  
가  
2  
FT-IR

