

Two-year survival analysis of twisted wire fixed retainer versus spiral wire and fiber-reinforced composite retainers: a preliminary explorative single-blind randomized clinical trial

Farhad Sobouti^a
Vahid Rakhshan^{b,c}
Mahdi Gholamrezaei Saravi^d
Ali Zamanian^d
Mahsa Shariati^e

^aDepartment of Orthodontics, Dental Faculty, Mazandaran University of Medical Sciences, Sari, Iran

^bThe Research Council, Iranian Tissue Bank and Research Center, Tehran University of Medical Sciences, Tehran, Iran

^cDepartment of Dental Anatomy and Morphology, Dental Branch, Islamic Azad University, Tehran, Iran

^dDepartment of Restorative Dentistry, Dental Faculty, Mazandaran University of Medical Sciences, Sari, Iran

^eCraniomaxillofacial Surgery Research Center, Tehran University of Medical Sciences, Tehran, Iran

Objective: Traditional retainers (both metal and fiber-reinforced composite [FRC]) have limitations, and a retainer made from more flexible ligature wires might be advantageous. We aimed to compare an experimental design with two traditional retainers. **Methods:** In this prospective preliminary clinical trial, 150 post-treatment patients were enrolled and randomly divided into three groups of 50 patients each to receive mandibular canine-to-canine retainers made of FRC, flexible spiral wire (FSW), and twisted wire (TW). The patients were monitored monthly. The time at which the first signs of breakage/debonding were detected was recorded. The success rates of the retainers were compared using chi-squared, Kaplan-Meier, and Cox proportional-hazard regression analyses ($\alpha = 0.05$). **Results:** In total, 42 patients in the FRC group, 41 in the FSW group, and 45 in the TW group completed the study. The 2-year failure rates were 35.7% in the FRC group, 26.8% in the FSW group, and 17.8% in the TW group. These rates differed insignificantly (chi-squared $p = 0.167$). According to the Kaplan-Meier analysis, failure occurred at 19.95 months in the FRC group, 21.37 months in the FSW group, and 22.36 months in the TW group. The differences between the survival rates in the three groups were not significant (Cox regression $p = 0.146$). **Conclusions:** Although the failure rate of the experimental retainer was two times lower than that of the FRC retainer, the difference was not statistically significant. The experimental TW retainer was successful, and larger studies are warranted to verify these results. [Korean J Orthod 2016;46(2):104-110]

Key words: Fixed orthodontic retainers, Multi-stranded wire, Fiber-reinforced composite, Ligature wire

Received June 10, 2015; Revised August 21, 2015; Accepted September 3, 2015.

Corresponding author: Mahsa Shariati.

Executive Editor, Craniomaxillofacial Surgery Research Center, 16 Azar St., North Kargar Ave., Tehran University of Medical Sciences, Tehran 14174, Iran.

Tel +98-2184901000 e-mail mahsa.shariati@gmail.com

*The study was self-funded by the authors and their institutions.

The authors report no commercial, proprietary, or financial interest in the products or companies described in this article.

© 2016 The Korean Association of Orthodontists.

This is an Open Access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/4.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

INTRODUCTION

The stability of the outcome of orthodontic treatment is a major clinical concern, as retraction of periodontal fibers might cause many cases to eventually relapse, particularly after alignment of the anterior teeth of the mandible.^{1,2} Many clinicians consider permanent or long-term retention to be the only way to maintain a proper post-treatment alignment.^{2,3} One method for maintaining long-term retention is to use fixed retainers that remain permanently in the mouth and are invisible, well tolerated, and do not require patient compliance after application by an orthodontist.^{2,4} Nevertheless, approximately 10% to 47% of fixed retainers fail because of wire fractures or bond failures.^{2,4-6}

Previously, fixed retainers were fabricated from thick stainless steel round wires and were later made from thinner coaxial or braided round wires.^{2,4,5} Recently, fiber-reinforced composite (FRC) resins were introduced as an alternative to stainless steel archwires to reduce the bulk of the lingual retainer.^{2,7-9} FRC retainers are flexible and able to easily conform to tooth surfaces. Additionally, they are esthetically accepted, nickel-free, biocompatible, and easily repairable.^{2,10-13} However, the main disadvantage is that FRC retainers produce a rigid splint that limits physiological tooth movement and may contribute to a higher failure rate.^{2,6}

The development of a method for long-term retention is important for treatment stability and to prevent further problems, such as incisor crowding.^{2,14,15} The most appropriate method for assessing retainer success is to perform a long-term randomized clinical trial. However, only a limited number of studies have been conducted to assess FRC retainers,^{2,13,16,17} and few studies have extended longer than 1 year.¹⁸ Furthermore, the results of previous studies do not favor any specific method, and there is no consensus on which method is the best.¹⁹⁻²¹

Both conventional wire retainers and FRC splints have specific disadvantages. Conventional retainers are made of active orthodontic wires and are thus rather technique-sensitive and time-consuming to position passively on the lingual surface. Additionally, these types of retainers can either debond or exert undesirable orthodontic forces on aligned teeth. FRC splints are expensive and even more technique-sensitive than conventional retainers. They may have higher failure rates, they are more difficult to repair, and they may cause additional periodontal conditions.^{2,6,17,22,23} Therefore, a more flexible yet strong wire design might be advantageous over the abovementioned types in terms of passivity (i.e., the ability to conform to the patient's dentition without exerting orthodontic force), the likeliness of debonding, cost, and chairside time. We

hypothesize that a retainer composed of twisted ligature wire might provide these advantages.

This 2-year prospective preliminary randomized clinical trial was conducted to compare the success rate of an experimental dead soft twisted wire (TW) retainer, which has not been assessed previously, with FRC and flexible spiral wire (FSW) retainers. The null hypothesis was that there would be no difference in the success rate between the three retainer types. Success was defined as the lack of any failure, ranging from a single-tooth debond to a total retainer breakage.

MATERIALS AND METHODS

This explorative, prospective preliminary single-blind randomized clinical trial originally enrolled 150 (50 × 3) fixed orthodontic patients who were monitored over 2 years. The sample size was predetermined as $n = 40 \times 3$ based on previous clinical research on retainers. To compensate for potential dropouts during the study period, three groups of 50 patients each were initially recruited.

Ethical considerations and potential harms

The study protocol was approved by the research committee of the research department of the university, in accordance with the Helsinki Declaration (ethical approval #2318). All patients (or their parents) were verbally informed of the purpose of the study, and they all signed routine informed consent forms. The subjects could request to change or remove the retainer (and leave the study) at any time during the study. No adverse events were identified during the study.

Subject screening and eligibility criteria

Patient recruitment was carried out in 2012 and 2013. The selected patients had been previously treated in a private office with standard MBT 0.022-inch (in) slot fixed appliances. The subjects were sequentially included based on the criteria described below and randomly assigned to one of the groups until each group reached 50 patients.

We included healthy participants who provided consent and had no history of previous dental extraction or orthognathic surgery, with an original indication for non-extraction treatment (Class I crowding, incisor mandibular plane angle [IMPA] < 92°, vertically normal or horizontal and no pattern of vertical excess, and with a crowding extent and soft tissue characteristics appropriate for non-extraction treatment). After the treatment period, patients were included if they had ideally aligned dentition, a Class I relationship with an overbite/overjet between 1 and 3 mm, no issues contraindicating or interfering with retention, clinical

signs suggesting bruxism or clenching, advanced dental abrasion/attrition/erosion, and a need for mandibular canine-to-canine fixed retention. We included patients who had good oral hygiene, healthy periodontal condition, and no previous history of using bonded retainers. The probing pocket depth was assessed and radiological examinations were performed to detect any periodontal problems. Patients with widespread probing depths more than 3 mm and radiographic evidence of periodontal bone loss were excluded.

Randomization and blinding

Random allocation was accomplished by the same orthodontist who enrolled the participants using a random number table. The study was single-blind: Each patient had layperson knowledge of his/her own retainer, but he/she had no knowledge (either technically or in layperson terms) of the other designs involved in the study.

Interventions

The experiments were performed using lingual canine-to-canine retainers, all bonded in a similar fashion, as described previously.^{22,24}

Retainer types

In the first group, 0.0175-in FSW (Ortosmail; Krugg Spa, Milan, Italy) was used. In the second group, an FRC splint (Everstick Ortho; Stick Tech, Turku, Finland) was used. In the third group, as described here for the first time, the retainers were fabricated by a left-handed orthodontist by carefully twisting two 0.009-in dead soft wires (Ligature wire; 3M Unitek, Monrovia, CA, USA) using a Mathieu plier to form a passive yet sufficiently strong bundle. The extent to which the wires were twisted (the number of twists per millimeter of wire) was similar between all specimens. The wires were twisted clockwise, 6 rounds per 10 mm. The bundle was formed against the lingual surface of the anterior teeth on a dental plaster.

Uniform bonding protocols

After scaling and polishing (using fluoride-free pumice) the lingual surface of the mandibular anterior teeth, full isolation was carried out using cheek retractors and cotton rolls in the labial and lingual areas. The surfaces were etched with 37% phosphoric acid (3M Unitek) for 40 seconds followed by 30 seconds of rinsing and then thorough air-drying with an oil-free syringe. Two layers of light-curable primer (Ormco, Orange, CA, USA) were added to the surface. Each layer was light-cured for 20 seconds (Optilux 501; Kerr Corp., Orange, CA, USA; light intensity, 930 mW/cm²; wavelength range, 400–505 nm). The retainers were prepared and contoured on plaster

casts.

A layer of resin (Transbond XT; 3M Unitek) was applied after placement to stabilize the retainer on the lingual surface, followed by light-curing for 20 seconds. Afterwards, a layer of restorative composite (Z100; 3M Unitek) was placed over the retainer and light-cured for 40 seconds. Finally, excess resin was removed from the interproximal areas using a scaler, and the restorations were polished.^{22,24} Each patient was instructed not to bite on hard or sticky foods with the anterior teeth to avoid disruption of the bonded retainers. The patients were thoroughly advised on this issue at the end of each visit.

Follow-up and retainer failure

Each patient was followed up once a month for 2 years or until the failure of the retainer. Retainer failure was defined as the first detachment of any composite pad or breakage/distortion of the retainer. Debonded retainers were routinely re-bonded or replaced depending on the severity of the case. The failure time was recorded for the survival analysis.

If a patient missed a follow-up session and visited the next month with an intact retainer, he/she remained in the study. However, if the retainer had failed during any period of absence lasting more than a month, the patient was excluded. Patients who stopped attending the follow-up sessions were excluded. The exclusion of a patient or the failure of a retainer did result in the discontinuation of treatment, as the patients continued to receive routine healthcare.

Statistical analysis

Descriptive statistics were calculated for each group. The ages were compared using an analysis of variance (ANOVA). The gender distributions were compared using a chi-squared test. The failure rates of the three groups of retainers were calculated using a Kaplan-Meier estimate and compared using a chi-squared test and a Cox proportional hazard regression using IBM SPSS Statistics ver. 20.0 (IBM Co., Armonk, NY, USA). The level of significance was set at 0.05.

RESULTS

More than 180 patients were assessed until 50 × 3 patients were included. Of the 150 enrolled patients, 22 were removed from the study because of failure to regularly attend the follow-up sessions. Finally, 42, 41, and 45 patients who received an FRC splint, an FSW retainer, or an experimental TDW retainer, respectively, were included in the analysis. The trial ended after 24 months of follow-up.

The mean age of the included patients was 18.0 ± 3.6 years (range, 13–25 years). The average ages were 18.5 ±

3.6, 18.4 ± 3.7 , and 17.0 ± 3.4 years, respectively, in the FRC, spiral flex, and TDW groups. The average ages were similar between the three groups, according to the ANOVA ($p = 0.102$). The FRC splint was used for 23 men and 19 women, the FSW retainer was used for 17 men and 24 women, and the TW retainer was used for 20 men and 25 women. The difference between the gender distributions of the groups was not significant (chi-squared $p = 0.441$).

Failure rates

All of the detachments occurred at the enamel junction. Of the FRC, FSW retainer, and TDW retainers, 15 (35.7%), 11 (26.8%), and 8 (17.8%) failed, respectively. Three FRC retainers, one FSW retainer, and one

TW retainer broke during the stud period, and the rest of the failures were caused by detachment. The chi-squared test failed to detect a significant difference in the failure rates between the groups ($p = 0.167$, Table 1).

Duration of successful retainer use

The average duration of success was approximately 21 months, according to the Kaplan–Meier estimates (Table 1). The Cox regression analysis showed no significant overall difference between the treatments ($p = 0.146$, Figure 1, Table 2), although a marginally significant difference was detected in the survival rates between the FRC and TDW retainers. A hazard ratio of 2.3 indicated that the risk of failure may be two times higher in the case of FRC retainers compared to TDW retainers, with a non-statistical trend ($p = 0.057$, Table 2). The risk of failure was approximately 50% less for TDW retainers compared to FSW retainers, though it was not statistically significant ($p = 0.317$).




Figure 1. Kaplan-Meier survival curves for each retainer type. FRC, Fiber-reinforced composite.

DISCUSSION

We did not observe an overall statistically significant difference between the success rates of the three retainer types. Nonetheless, the experimental retainers showed better survival results compared to the FRC retainers. Similar to metallic alloys, fibers might offer superior mechanical properties, while composite resins provide esthetic benefits.^{6,22,25,26} Considering the increasing number of adult patients seeking orthodontic treatment, esthetics is now a major factor contributing to patient satisfaction.^{22,27}

FRC retainers have advantages, including biocompatibility (no metal content), making them safe for patients

Table 1. Survival time statistics calculated using the Kaplan-Meier analysis

Treatment	Success	Fail	Mean failure time (mo)	SE	95% CI	
FRC	27 (64.3%)	15 (35.7%)	19.952	0.991	18.010	21.894
Flexible spiral wire	30 (73.2%)	11 (26.8%)	21.366	0.893	19.616	23.115
Twisted wire	37 (82.2%)	8 (17.8%)	22.356	0.690	21.003	23.709
Overall	94 (73.4%)	34 (26.6%)	21.250	0.496	20.277	22.223

SE, Standard error; CI, confidence interval; FRC, fiber-reinforced composite.

Table 2. The results of the Cox regression, comparing FRC and FSW with the twisted wire as the reference

Treatment	B	SE	Wald χ^2	p-value	HR	95% CI for HR	
FRC	0.835	0.438	3.632	0.057	2.304	0.977	5.437
FSW	0.465	0.465	1.000	0.317	1.591	0.640	3.957

FRC, Fiber-reinforced composite; FSW, flexible spiral wire; B, regression coefficient; SE, standard error; HR, hazard ratio; CI, confidence interval.

who are allergic to metals or who are undergoing MRI assessments, and FRC retainers can be bonded to dental tissues.^{22,28} FRCs have been introduced in dental practice in recent years. The possibility of reinforcing composite resins with fibers such as aramid, polyethylene, carbon, or glass has numerous clinical applications, including the replacement of missing teeth, repair of complete dentures, preparation of overdenture parts, splinting of periodontal teeth, use in Maryland Bridges, or the direct construction of posts and cores.^{13,22,29} The flexural strength of FRCs might be similar to that of gold and Cr-Co alloys and greater than that of stainless steel.^{22,25,30} In orthodontic treatment, FRCs have passive and active applications, such as post-orthodontic tooth retention and anchorage unit increases.^{6,22,26} Glass FRCs are recommended for post-orthodontic fixed lingual retention in the anterior segment.^{6,22,25,26} The clinical efficacy of FRC retainers may be based on the internal structure of the complex. The resin of the matrix and the adhesive system integrate with fibers. The homogeneous structure of integrated resin matrix, adhesive, and fiber might absorb and dissipate mechanical stresses.^{6,22,25,26,30} Conventional retainers use mechanical retention between non-bondable materials, such as metal and composite adhesives, creating a point of weakness at the junction between different materials.^{6,22,25,26} Multistranded FSWs are broadly accepted for routine use in modern orthodontics.^{6,17,22,26}

Both FRCs and multi-stranded wires used for post-orthodontic retention have shown 2-year success rates of approximately 50% to 90%.^{17,22,28,30} In this regard, our findings are consistent with studies reporting better results with multi-stranded wires compared to FRC retainers, such as polyethylene ribbon-reinforced or glass fiber-reinforced (GFR) retainers, *in vivo*^{13,17} or *in vitro*.¹⁶ For instance, the average success durations were approximately 24 and 12 months for multi-stranded and FRC retainers, respectively.¹³ Another study showed significantly higher success rates for multi-stranded retainers (88%) compared to GFR retainers (49%).¹⁷ FRC retainers might have a higher failure rate because of their lower flexibility, which results in higher strain in the inter-dental areas under loading.^{2,31} This can lead to a higher probability of microfracture or debonding, particularly in the case of teeth that have become more mobile after orthodontic treatment.^{2,13,17,31,32} Other chemomechanical properties, such as water sorption and thermal expansion of polyethylene materials, might also contribute to the higher failure rates of FRC retainers.^{2,13} Capillary forces might cause water to enter non-polymerized voids along the woven fibers and alter the mechanical characteristics.^{2,13} Moreover, the lingual placement of FRC, which is necessary for esthetic reasons, is not the best option to reinforce

a composite.^{17,33-35} Furthermore, FRC retainers are technique-sensitive, which may indicate higher rate of human error.¹⁷ Multi-stranded retainers have suitable efficacy and reliability; hence, they are considered a standard treatment option in modern orthodontics.^{2,4,5} Despite the success of multi-stranded retainers, splinting the teeth with an FRC is also a popular choice.^{2,12} On the other hand, the results of the present study are in contrast to some previous studies showing insignificant differences between multi-stranded metal wires and FRC retainers.^{2,22,28} The discrepancies might be attributable to the use of different materials and methodologies, including differences in the method used for light curing (light-emitting diode versus quartz-tungsten halogen), which might affect the polymerization, or differences in the interval for follow-up (6-month follow-up visits versus monthly follow-up visits).²²

This study was limited by several factors. It would be preferable to include more specimens (based on power calculations) and to evaluate other FRC designs and maxillary retainers for a longer duration. The insufficient sample size makes this study inconclusive. In addition, if the sample size were increased, a *p*-value less than 0.05 might be obtained in the comparison between FRC and TDW, which resulted in a *p*-value of 0.057 in this study. It should be noted, however, that conducting a 2-year pilot study for a retainer type that has not been previously investigated could postpone such a project for another 2 or 3 years. Therefore, the authors decided to conduct this trial without a pilot study. Moreover, although we considered numerous inclusion/exclusion criteria to ensure a uniform sample, the control of patient factors was lacking. It would be preferable to also control for chewing habits, vertical skeletal patterns, and inclination of the lower incisors, which might influence the success rate.

This study was advantageous in terms of the use of standardized materials for bonding,²² the well-balanced groups and homogenous randomization of the treatments,¹⁷ and the introduction of a successful retainer, which might be more flexible than the traditional spiral wires. Nevertheless, the mechanical properties of this new retainer should be assessed and optimized in follow-up *in vitro* studies. Moreover, although the orthodontist made efforts to exert a similar force while twisting the dead wires, it was impossible to standardize this factor without the use of automatic machinery. Still, the wires were twisted the same number of times per unit of length. The generalizability of this study is improved due to the recruitment of subjects of both genders and of different ages. However, the findings are only generalizable to the mandible and to the material brands used (results achieved with a particular brand are less likely to be generalizable to

other brands). Future studies should also evaluate the gingival response to the experimental retainer.

CONCLUSION

Within the limitations of this preliminary clinical trial, the three types of retainers, including the experimental retainer created by twisting two dead soft wires, appear to present similar success rates within a 2-year follow-up period. The survival rate of the experimental TW retainers might be better than that of the FRC retainers, although we cannot decisively conclude this from a statistical point of view, and future studies with larger samples are necessary to confirm or reject the success of this retainer and to assess the gingival response. Although the superiority of the TDW retainer over the FRC could not be confirmed, the results show that the TW retainer was at least equivalent to the FRC.

ACKNOWLEDGEMENTS

Farhad Sobouti designed the experimental retainer, proposed, designed, and performed the study, provided the data, and participated in drafting the methods section. Vahid Rakhshan searched the literature, designed and performed the statistical analyses, prepared the figure, and drafted/revised the paper. Mahdi Gholamrezaei Saravi, Ali Zamanian, and Mahsa Shariati searched the literature and/or designed the study.

REFERENCES

- Littlewood SJ, Millett DT, Doubleday B, Bearn DR, Worthington HV. Retention procedures for stabilising tooth position after treatment with orthodontic braces. *Cochrane Database Syst Rev* 2006;(1):CD002283.
- Salehi P, Zarif Najafi H, Roeinpeikar SM. Comparison of survival time between two types of orthodontic fixed retainer: a prospective randomized clinical trial. *Prog Orthod* 2013;14:25.
- Störmann I, Ehmer U. A prospective randomized study of different retainer types. *J Orofac Orthop* 2002;63:42-50.
- Zachrisson BU. Clinical experience with direct-bonded orthodontic retainers. *Am J Orthod* 1977; 71:440-8.
- Zachrisson BU. The bonded lingual retainer and multiple spacing of anterior teeth. *Swed Dent J Suppl* 1982;15:247-55.
- Bearn DR. Bonded orthodontic retainers: a review. *Am J Orthod Dentofacial Orthop* 1995;108:207-13.
- Torkan S, Oshagh M, Khojastepour L, Shahidi S, Heidari S. Clinical and radiographic comparison of the effects of two types of fixed retainers on periodontium - a randomized clinical trial. *Prog Orthod* 2014;15:47.
- Geserick M, Ball J, Wichelhaus A. Bonding fiber-reinforced lingual retainers with color-reactivating flowable composite. *J Clin Orthod* 2004;38:560-2.
- Orchin JD. Permanent lingual bonded retainer. *J Clin Orthod* 1990;24:229-31.
- Meiers JC, Duncan JP, Freilich MA, Goldberg AJ. Preimpregnated, fiber-reinforced prostheses. Part II. Direct applications: splints and fixed partial dentures. *Quintessence Int* 1998;29:761-8.
- Iniguez I, Strassler HE. Polyethylene ribbon and fixed orthodontic retention and porcelain veneers: solving an esthetic dilemma. *J Esthet Dent* 1998;10:52-9.
- Karaman AI, Kir N, Belli S. Four applications of reinforced polyethylene fiber material in orthodontic practice. *Am J Orthod Dentofacial Orthop* 2002;121: 650-4.
- Rose E, Frucht S, Jonas IE. Clinical comparison of a multistranded wire and a direct-bonded polyethylene ribbon-reinforced resin composite used for lingual retention. *Quintessence Int* 2002;33:579-83.
- Durbin DD. Relapse and the need for permanent fixed retention. *J Clin Orthod* 2001;35:723-7.
- Renkema AM, Al-Assad S, Bronkhorst E, Weindel S, Katsaros C, Lisson JA. Effectiveness of lingual retainers bonded to the canines in preventing mandibular incisor relapse. *Am J Orthod Dentofacial Orthop* 2008;134:179e1-8.
- Foek DL, Ozcan M, Krebs E, Sandham A. Adhesive properties of bonded orthodontic retainers to enamel: stainless steel wire vs fiber-reinforced composites. *J Adhes Dent* 2009;11:381-90.
- Tacken MP, Cosyn J, De Wilde P, Aerts J, Govaerts E, Vannet BV. Glass fibre reinforced versus multi-stranded bonded orthodontic retainers: a 2 year prospective multi-centre study. *Eur J Orthod* 2010; 32:117-23.
- Edman Tynelius G, Bondemark L, Lilja-Karlander E. Evaluation of orthodontic treatment after 1 year of retention--a randomized controlled trial. *Eur J Orthod* 2010;32:542-7.
- Lai CS, Gossen JM, Renkema AM, Bronkhorst E, Fudalej PS, Katsaros C. Orthodontic retention procedures in Switzerland. *Swiss Dent J* 2014;124:655-61.
- Horton JK, Buschang PH, Oliver DR, Behrents RG. Comparison of the effects of Hawley and perfector/spring aligner retainers on postorthodontic occlusion. *Am J Orthod Dentofacial Orthop* 2009; 135:729-36.
- Rowland H, Hichens L, Williams A, Hills D, Killingback N, Ewings P, et al. The effectiveness

- of Hawley and vacuum-formed retainers: a single-center randomized controlled trial. *Am J Orthod Dentofacial Orthop* 2007;132:730-7.
22. Sfondrini MF, Fraticelli D, Castellazzi L, Scribante A, Gandini P. Clinical evaluation of bond failures and survival between mandibular canine-to-canine retainers made of flexible spiral wire and fiber-reinforced composite. *J Clin Exp Dent* 2014;6:e145-9.
 23. Radlanski RJ, Zain ND. Stability of the bonded lingual wire retainer—a study of the initial bond strength. *J Orofac Orthop* 2004;65:321-35.
 24. Artun J, Spadafora AT, Shapiro PA. A 3-year follow-up study of various types of orthodontic canine-to-canine retainers. *Eur J Orthod* 1997;19:501-9.
 25. Vallittu PK. Flexural properties of acrylic resin polymers reinforced with unidirectional and woven glass fibers. *J Prosthet Dent* 1999;81:318-26.
 26. Bearn DR, McCabe JF, Gordon PH, Aird JC. Bonded orthodontic retainers: the wire-composite interface. *Am J Orthod Dentofacial Orthop* 1997;111:67-74.
 27. Sobouti F, Rakhshan V, Chiniforush N, Khatami M. Effects of laser-assisted cosmetic smile lift gingivectomy on postoperative bleeding and pain in fixed orthodontic patients: a controlled clinical trial. *Prog Orthod* 2014;15:66.
 28. Bolla E, Cozzani M, Doldo T, Fontana M. Failure evaluation after a 6-year retention period: a comparison between glass fiber-reinforced (GFR) and multistranded bonded retainers. *Int Orthod* 2012;10:16-28.
 29. Ferreira ZA, de Carvalho EK, Mitsudo RS, Bergamo PM. Bondable reinforcement ribbon: clinical applications. *Quintessence Int* 2000;31:547-52.
 30. Chong KH, Chai J. Strength and mode of failure of unidirectional and bidirectional glass fiber-reinforced composite materials. *Int J Prosthodont* 2003;16:161-6.
 31. Artun J. Caries and periodontal reactions associated with long-term use of different types of bonded lingual retainers. *Am J Orthod* 1984;86:112-8.
 32. Tanaka E, Ueki K, Kikuzaki M, Yamada E, Takeuchi M, Dalla-Bona D, et al. Longitudinal measurements of tooth mobility during orthodontic treatment using a periotest. *Angle Orthod* 2005;75:101-5.
 33. Chung K, Lin T, Wang F. Flexural strength of a provisional resin material with fibre addition. *J Oral Rehabil* 1998;25:214-7.
 34. Dyer SR, Lassila LV, Jokinen M, Vallittu PK. Effect of fiber position and orientation on fracture load of fiber-reinforced composite. *Dent Mater* 2004;20:947-55.
 35. Ellakwa AE, Shortall AC, Shehata MK, Marquis PM. The influence of fibre placement and position on the efficiency of reinforcement of fibre reinforced composite bridgework. *J Oral Rehabil* 2001;28:785-91.